

Simulation of the Mechanical Properties of Snow and Mud Using Uintah

Jonah H. Lee

Department of Mechanical Engineering
University of Alaska Fairbanks


April 2, 2009

5th MPM Workshop, Corvallis, Oregon State University

Outline

- Application and Motivation
- Mud
- Snow
- Future Work

Application: Vehicle-Snow/Mud Interaction




Source: Dr. Sally Shoop, CRREL


Motivation

Large Uncertainties in Material Properties of Soft Terrains

- Environmental conditions dictate terrain composition (e.g., snow metamorphism – a sintering *process*).
- Process determines *microstructure*
- Microstructure determines *properties*
 - Mechanical (elasticity, viscoplasticity, damage, fracture...)
 - Physical (thermal conductivity, permeability, dielectric constant...)



Example: Large Uncertainties in Snow Properties




$e, \sigma = 35.16 \text{ kPa}.$

Figure 6 (cont'd). Shear stress versus initial snow density for various normal loads (shear annulus).

Source: CRREL CR90-9

Example: Large Uncertainties in Tire-Snow Interaction Interfacial Forces (Li et al., 2009)



Scientific Question

How does one address the large uncertainties in the mechanical properties of soft terrains?

- 1. Study the microstructure of materials**
- 2. Study micro-scale properties of materials as a function of microstructure**


The 'Big' Picture

- Multiscale stochastic studies
 - Link micro-, meso- and macroscale properties
 - Link multiscale material properties to multiscale terrain topologies
 - Incorporate results into vehicle design with uncertainties
- Key technical fields
 - Stochastic geometry
 - Stochastic mechanics
 - Reliability

Why Study Mud (Saturated Soil)?

- Tire companies group snow and mud together
- Provides a baseline for
 - Unsaturated soils
 - Frozen and thawed soils

Domain of Saturated Soil (void ratio = 0.338; depth = 0.012 m)



Modeling of Saturated Soil as a Fluid-Structure Interaction Problem – Uintah Explicit

- Soil grains modeled as circular cylinders packed in a regular array
- Radius of each grain varies randomly in $[0.75 \text{ radius}, \text{radius}]$ (radius=1 mm)
- Each soil grain is discretized into material points
- Soil grain is modeled as an elastic material
- Gaps between the soil grains are filled with interstitial water, also discretized into material points
- Plane strain deformation

Constitutive Equations for Nearly Incompressible Water

$$\sigma_{ij} = -p\delta_{ij} + 2\mu d'_{ij}$$

d'_{ij} = rate of deformation tensor

$$p = k \left[\left(\frac{\rho}{\rho_0} \right)^\gamma - 1 \right]$$

ρ_0, ρ = initial and final density

k, γ = material constants

Material Properties

Solid:


Density	2,000 [kg / m^3]
Bulk modulus	39.585 [GPa]
Shear modulus	18.27 [GPa]
Friction coefficient	0.5

Water:

Density	1,000 [kg / m^3]
μ	0.001 [Pa-sec]
γ	7
k	2.2 [GPa]


Load-Displacement Curves of Saturated and Dry Soils under Unconfined Compression – 6.18 m/s

Initiation of instability




Residual strength

PDF of Equivalent Stress Near Peak Stress




Load-Displacement Curves of Indentation Tests

Indenter Width 3.125 cm




Saturated





Dry

Deterministic Macro-Scale Snow Model



- Drucker-Prager Cap Model (After Shoop, 2001) for Fresh (Low-Density) Snow



Abaqus/CAE Tire Model



Macro-Scale Plate and Static Tire Indentations with Frictional Contact (Density = 200 kg/m³)



Abaqus Explicit and Updated Lagrangian Scheme

Macro-Scale Pressure-Sinkage Relationship





Plate Indentation



Static Tire Indentation

Source: J.H. Lee, J. Terramechanics (2009)


Addressing Uncertainty of Snow by Understanding Effects of Microstructure

- Collect snow samples from field
- Store snow in a freezer at -25 C
- Conduct 3D X-Ray MicroTomography
- Large-scale numerical simulations of indentation and other tests and compare with experimental results

Skyscan 1172 Microtomography




Snow Sample Holder



Diameter 1
cm

Segmentation Using ImageJ



grey-level




Black is ice


binarized image

Example of Snow Microstructure

Side Length = 3.618 mm



Viscoplastic Ice Model with Damage



Source: Kircher, Huang, Lee, August 2008

Viscoplasticity

SUVIC-I (Aubertin and Lee)

- Strain rate history-dependent **Unified Viscoplastic** model with Internal variables for **Crystalline materials – Ice**
- Isotropic polycrystalline ice (**“snow ice”**) at

$$T \geq -55^{\circ}C; 10^{-8} \leq \dot{\epsilon} \leq 10^{-2} s^{-1}; 0.04\text{MPa} \leq \sigma_{equiv} \leq 20\text{MPa}$$

- **Unified model** – plasticity, creep and their interactions are modeled in the same way
- Three **internal variables**: back stress (kinematic hardening), yield and drag stress (isotropic hardening)
- Evolution of the state variables: combined action of hardening, dynamic recovery
- **Viscoplastic** – introduction of a yield surface makes a clear distinction between elastic and inelastic behavior.

Summary of SUVIC-I

$$\dot{\epsilon}_{ij} = \dot{\epsilon}_{ij}^e + \dot{\epsilon}_{ij}^i; \quad \dot{\epsilon}_{ij}^e = \frac{\dot{S}_{ij}}{2G} + \frac{\dot{\sigma}_{kk}}{9K} \delta_{ij}.$$

$$\dot{\epsilon}_{ij}^i = A \left\langle \frac{X_{ae} - R}{K} \right\rangle^N n_{ij} \exp\left(-\frac{Q}{R_g T}\right), \quad n_{ij} = \frac{3}{2} \frac{S_{ij} - B_{ij}}{X_{ae}},$$

$$X_{ae} = \sqrt{\frac{3}{2} (S_{ij} - B_{ij})(S_{ij} - B_{ij})}$$

$$\dot{\epsilon}_e^i = \sqrt{\frac{2}{3} \dot{\epsilon}_{ij}^i \dot{\epsilon}_{ij}^i} = A \left\langle \frac{X_{ae} - R}{K} \right\rangle^N \exp\left(-\frac{Q}{R_g T}\right)$$

- Decomposition of elastic and inelastic strain rate
- Inelastic strain rate a function of back stress (B), yield stress (R), drag stress (K) and temperature
- X (reduced stress)

Summary of SUVIC-I (cont.)

$$\dot{B}_{ij} = \frac{2}{3} A_1 \dot{\epsilon}_{ij}^i - \frac{A_1}{B_e'} B_{ij}, B_e' = B_0 \left(\frac{\dot{\epsilon}_e^i}{\dot{\epsilon}_0} \right)^{\frac{1}{n}}$$

$$\dot{R} = A_3 \dot{\epsilon}_e^i \left(1 - \frac{R}{R'} \right), \dot{K} = A_5 \dot{\epsilon}_e^i \left(1 - \frac{K}{K'} \right).$$

$$R' = R_0 \left(\frac{\dot{\epsilon}_e^i}{\dot{\epsilon}_0} \right)^{\frac{1}{n}}, K' = \left(\frac{\dot{\epsilon}_e^i}{A \exp \left(-\frac{Q}{R_g T} \right)} \right)^{\frac{1}{N}} (X_{ae}' - R')$$

$$X_{ae}' = \sigma' - B_e'; \sigma' = \sigma_0 \left(\frac{\dot{\epsilon}_e^i}{\dot{\epsilon}_0} \right)^{\frac{1}{n}}$$

- Evolution of back stress (B), yield stress (R) and drag stress (K)
- Saturation values of state variables (i.e., steady-state creep state)


Numerical Integration: Theta family Taylor series expansion

$$\Delta \mathcal{E}^i = \Delta t \left[(1 - \theta) \dot{\mathcal{E}}_t^i + \theta \dot{\mathcal{E}}_{t+\Delta t}^i \right]; 0 \leq \theta \leq 1$$

$$\dot{\mathcal{E}}_{t+\Delta t}^i = \dot{\mathcal{E}}_t^i + \sum_i \frac{\partial \dot{\mathcal{E}}^i}{\partial \beta_i} \dot{\beta}_i \Delta t.$$

$$\dot{\sigma}_{ij} = \left[L_{ijkl} - \frac{\xi}{1+\xi} \frac{1}{\bar{H}} P_{ij} Q_{kl} \right] \dot{\mathcal{E}}_{kl} - \frac{\dot{\mathcal{E}}_t^i}{1+\xi} P_{ij}.$$

Indentation Configuration






Snow Model (Low-Density)


- Original size 612x612x498 pixels
- Each pixel is 12 μm
- VOI used is 400x400x400 pixels
- Down sampled to 100x100x100 pixels using ImageJ
 - Each pixel is 48 μm
- Uintah utility pfs2 to convert voxels into material points for multiple processors
- Indentation speed is 48 mm/sec.
- Visualization using SCIRun

Indenter and Initial Snow Geometry



8 Processors – Uintah Explicit




Final Snow Geometry




Failed Ice Particles vs. Time



Load-Displacement Relationship



Pressure-Displacement Relationship



Animation of Progressive Failure of Particles

Examples of Future Work



- Snow/Soils penetration tests
- Traction tests of rubber on snow/soils
- Triaxial tests of snow/soils
- Frozen sands



**Micro-CT imaging &
mechanical testing**



**Micro-CT imaging &
SnowMicroPenetrometer
testing**



Acknowledgements

- Jim Guilkey and the Uintah team
- Daisy Huang – X-Ray MicroTomography Snow Images
- Automotive Research Center led by University of Michigan
- U.S. Army TARDEC
- Arctic Region Supercomputing Center (ARSC) at UAF

Thank You!

Questions?